

TABLEAU DE CORRESPONDANCE DES DIATOMEES

Marques⇒	CECA	DICALITE	EAGLE PICHER	LAFFORT OENOLOGIE	LAFFORT OENOLOGIE	LAFFORT OENOLOGIE	SPINDAL
Origine⇒	<i>France</i>	<i>U.S.A.</i>	<i>U.S.A.</i>	<i>Europe</i>	<i>France</i>	<i>Europe</i>	<i>Europe</i>
Perméabilité moyenne (Darcy) ↓	CLARCEL ↓	↓	CELATOM ↓	CELITE ↓	DIATOMYL ↓	↓	SPINDALITE ↓
0.02		215 SUPERAID					L
	CBL 3				P6		
			FP-1SL				N XX
	CBL	UF			P5		
0.1						STANDARD SUPERCEL	
	CBR						R
0.2		SPEEDFLOW			P4		
0.3	CBR 3		FP-4				
		231					
0.4		341					
0.9						HYFLO SUPERCEL	
	DIF / BO	SPEEDPLUS	FW-12		P2		
	DIC / B	375					
1.5	DIC	SPEEDEX			P1		
2.1		2500	FW-20				
2.7							
	DIC 3 s						
3.2	DIC / S						AM
		4200		535	P0		
4		4500		545	P00		
	DIT R	5000	FW50				
7		6000					
9		7000					
	DIT / 2R						TT
15							